

PRODUCT DATA

9 09 67 23 **Resinous
Flooring**

DEGADUR® 523

Industrial strength methyl-methacrylate topcoat resin for pigmented flooring systems

Description

DEGADUR® 523 is a methyl-methacrylate topcoat resin for use within the SRS DEGADUR® flooring systems. DEGADUR® 523 is a solvent free, 2-component, 100% reactive resin that is ideal for roller applied coatings and pigmented flooring systems. DEGADUR® 523 is a medium viscosity resin that is ideal for use as a pigmented topcoat that can be applied in a single application. DEGADUR® 523 is colorless, so the DEGADUR® Pigment will be necessary for pigmented flooring systems. DEGADUR® 523 can also be used as a topcoat for decorative systems requiring a clear topcoat.

Yield

All coverage rates are approximate. Coverage rates will vary with the desired texture and porosity of substrate. Please refer to individual flooring system data sheets for coverage rate information.

Packaging

50 gallon drum

Color

Transparent

See Performance Flooring Color Chart for pigment color offerings.

Features

- Fully cures in one hour
- Superior chemical resistance
- High viscosity resin
- Can be applied at 30° F (-3.6° C)

Shelf Life

2 years when properly stored

Storage

Keep stored in cool, dry environment, and out of direct sunlight.

Where to Use

APPLICATION

- Used as a topcoat within the following SRS DEGADUR® flooring systems:
 - Degaclad™ CP
 - Degaflex™ CP

Please refer to individual flooring system data sheets for application instructions.

Every SRS DEGADUR® flooring system is a multiple component system that utilizes a methyl-methacrylate (MMA) resin. It is critical that the instructions listed in the Material Safety Data Sheet and on the product label for every component of the system be read, understood and followed. MMA resins are flammable liquids in their uncured state. Smoking, open flames or sparks should not be permitted during the handling of the product. Explosion safe ventilation must be used during the application to minimize vapor collection in the installation area and to improve overall air quality for the crew. All foodstuffs must be removed during installation of the flooring system.

Benefits

- Reduction in downtime and rapid return to service
- Can withstand exposure to harsh chemicals
- Topcoat that can be applied in a single application
- Can perform installations in cooler temperatures

Health, Safety and Environmental

Read, understand and follow Material Safety Data Sheets and product labels for all components of this flooring system prior to use. The MSDS can be obtained by searching for them on www.BuildingSystems.BASF.com, e-mailing your request to basfbcsct@basf.com or calling 800/433-9517. Use only as directed.

Test Data

PROPERTY	RESULTS	TEST METHODS
Percentage Reactive Resin	100%	
Percentage Solids	100%	
Water Absorption, (%/24 hours)	0.05	ASTM D570
Hardness (Shore D)	80	ASTM D2240
Viscosity	300 – 400 cps	ASTM D2393
Taber Abrasion Resistance (mg. Loss, 1000 cycles, CS17 Wheel)	74	ASTM D4060

Please refer to BASF Performance Flooring Chemical Resistance Chart for further information.

® = registered trademark
DEGADUR® = trademark of Evonik Röhm GmbH, Darmstadt / Germany

BASF Corporation Building Systems

889 Valley Park Drive
Shakopee, MN, 55379

www.BuildingSystems.BASF.com

Customer Service 800-433-9517
Technical Service 800-243-6739



LIMITED WARRANTY NOTICE: Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

For professional use only. Not for sale to or use by the general public.

Form No. 1027363 1/11
Printed on recycled paper including 10% post-consumer fiber.

© 2011 BASF
Printed in U.S.A.