



PRODUCT PROFILE

- GENERIC DESCRIPTION** Colored Quartz-Filled Modified Polyamine Epoxy
- COMMON USAGE** A decorative broadcast or slurry broadcast laminated floor-topping system installed at 1/8" minimum thickness. Protects against impact, abrasion and mild chemicals with an aesthetically pleasing appearance.
- COLORS** Available in 12 standard colors. Refer to StrataShield Decorative Quartz Color card. Custom colors also available. **Note:** Epoxies chalk and yellow with age, extended exposure to UV and artificial lighting. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause amine blush, possibly affecting adhesion of subsequent topcoats.
- FINISH** Decorative quartz—multi-colored appearance. The finished appearance will depend on the type, film thickness and number of the clear finish coats selected.

COATING SYSTEM

- SURFACER/FILLER/PATCHER** Series 63-1500, 206, 218, 219. **Note:** A repair kit of 201, with Part C fumed silica, is available for small patching/surfacing repairs. For more extensive repairs and additional information, contact your Tnemec representative or Tnemec Technical Services.
- PRIMERS** **Concrete:** Self-priming or Series 201
- TOPCOATS** Series 284, 285, 295. **Note:** If Series 285 or 295 is selected for the finish coat, an intermediate coat of Series 284 is required. Refer to the StrataShield Installation and Application guide for floors.

SURFACE PREPARATION

- CONCRETE** Prepare surfaces by method suitable for exposure and service. Refer to the appropriate primer data sheet for specific recommendations.
When self-priming: Allow new concrete to cure 28 days. Verify dryness by testing for moisture with a "plastic film tape-down test." (Reference ASTM D 4263) Should moisture be detected, perform "Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride." (Reference ASTM F 1869) Moisture content not to exceed three pounds per 1,000 sq ft in a 24 hour period. Shot-blast or mechanically abrade to remove laitance, curing compounds, hardeners, sealers and other contaminants and to provide surface profile. Large voids, bugholes and other cavities should be filled with recommended filler or surfacer. (Reference SSPC-SP13, ICR1 CSP3-5)
- ALL SURFACES** Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

- VOLUME SOLIDS** 100% (mixed)
- RECOMMENDED DFT** Minimum of 1/8". Requires two broadcast applications at 1/16" each or applied as a slurry broadcast.
- CURING TIME**

Temperature	Between Broadcasts/Topcoats	Place in Service
75°F (24°C)	12 to 24 hours	24 hours

- VOLITILE ORGANIC COMPOUNDS** **Unthinned:** 0.15 lbs/gallon (18 grams/litre)
- THEORETICAL COVERAGE** 1,604 mil sq ft/gal (39.4 m²/L at 25 microns). See APPLICATION for coverage rates.
- NUMBER OF COMPONENTS** Three—Liquids: Part A & Part B (2 Parts A to 1 Part B by volume). Colored quartz: Part C
The Part C colored quartz (ChromaQuartz) is available from Tnemec or can be purchased from a different supplier.

PACKAGING

	PART A	PART B	Yield (mixed)
Extra Large Kit	2-55 gallon drums	1-55 gallon drum	165 gallons
Large Kit	2-5 gallon pails	1-5 gallon pail	15 gallons
Small Kit	2-1 gallon cans	1-1 gallon can	3 gallons

The Part C colored quartz aggregate is based on a nominal amount calculated at one-half pound per sq ft (2.4 kg/m²) per broadcast application or one pound per sq ft (4.8 kg/m²) for a double broadcast. Additional colored quartz aggregate may be required to accommodate for waste or loss during application or to make coving material.

- NET WEIGHT PER GALLON** 9.33 ± 0.25 lbs (4.23 ± .11 kg) mixed
- STORAGE TEMPERATURE** Minimum 40°F (4°C) Maximum 90°F (32°C)
- TEMPERATURE RESISTANCE** (Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)
- SHELF LIFE** 12 months at recommended storage temperature.
- FLASH POINT - SETA** N/A
- HEALTH & SAFETY**

This product contains chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

DECO-TREAD® | SERIES 222

APPLICATION

COVERAGE RATES	<p>Before commencing, obtain and thoroughly read the StrataShield Installation and Application Guide for floors.</p> <p>The mixed liquids (Part A and B) are spread at a rate of 80 sq ft (7.4 m²) per gallon or approximately 20 mils (510 microns) wet. The colored quartz aggregate is then broadcast into the liquid until a uniformly dry appearance is obtained. After the first broadcast layer cures, forming a thickness approximately 1/16" (1.6 mm) thick, the excess colored quartz is removed and a second application is repeated to obtain a minimum thickness of 1/8" (3.2 mm).</p> <p>Note: A double broadcast is required to achieve the 1/8" (3.2 mm) minimum. For slurry application instructions and spreading rates contact your Tnemec representative.</p>
MIXING	<p>Use a variable speed drill with a PS Jiffy blade. Slowly mix 2 parts A component, and while under agitation add 1 part B component and mix for a minimum of two minutes. Ensure that all Part B is blended with Part A by scraping the pail walls with a flexible spatula.</p> <p>Note: A large volume of material will set up quickly if not applied or reduced in volume.</p> <p>Caution: Do not reseal mixed material. An explosion hazard may be created.</p>
THINNING	Normally not required.
POT LIFE	25 to 30 minutes at 75°F (24°C)
APPLICATION EQUIPMENT	Squeegee or trowel and backroll. For detailed instructions, refer to the StrataShield Installation and Application Guide for floors.
SURFACE TEMPERATURE	Minimum of 55°F (13°C), optimum 65°F to 80°F (18°F to 27°C), maximum of 90°F (32°C). The substrate temperature should be at least 5°F (3°C) above the dew point.
MATERIAL TEMPERATURE	For optimum application, handling and performance, the material temperature during application should be between 70°F and 90°F (21°C and 32°C). Temperature will affect the workability. Cool temperatures increase viscosity and decrease workability. Warm temperatures will decrease viscosity and shorten pot life.
CLEANUP	Flush and clean all equipment immediately after use with xylene or MEK.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.